

❖ Product Description

- | | |
|---|---|
| I. The wire exhibits excellent mechanical properties of weld metal and good toughness characteristics | II. Specially made for high strength steels |
| | III. Radiographic weld quality |

❖ Range of Application

- | | |
|--|--|
| I. For welding steels with minimum yield strength upto 890MPa and minimum tensile strength of 950MPa | equipment, industrial truck welding, cranes, lifts in buildings etc. |
| II. Very suitable and suitable for welding of heavy machineries such as earth moving | III. Suitable for high stressed structural components |

❖ % Classification

- AWS/SFA 5.28 ER120S-G

❖ Chemical Composition

- As agreed between supplier and purchaser

❖ Mechanical Properties of all weld metal

Condition	UTS, Mpa (Min)	YS, Mpa (Min)	% Elongation	Charpy "v" Notch Impact @ 0°C
As Welded	830	-	-	-

❖ Wire Size & Weld Position

- Diameter in mm-1.6, 2.0 2.40,3.20,4.00 and 5.00.
- All position

❖ Current and Gas- Flow Rate

- DCEN & 8-15 lit/min

❖ Packaging

Sizes available in cut length of 1000mm	1.60,2.00,2.40,3.20,4.00,5.00			
Packing Code	A		B	
Packing Available	5kg PLASTIC TUBE	20KG BOX	10KG PAPER TUBE	20KG BOX
Net Weight of Wire	5	20	10	20

Special Note: -

All the value above mentioned are typical values.

- (1) All the value above mentioned are typical values
- (2) Usually all chemistry and mechanical properties will depend on actual wire chemistry and arc voltage used for welding.

SHAKUNT ENTERPRISES PRIVATE LIMITED

Corporate Office: - 619/A, EMMAR DIGITAL GREEN, 6th Floor, Sector-61, GURUGRAM (HARYANA)-122102
E-Mail:- info@shakunt.com

Ludhiana Works:- B-XXIX-595/5,Campa Cola Road,Dhandari Kalan Industrial Area-C,Ludhiana (PUNJAB) **INDIA**

Dharwad Works:- Plot no.577 C & D,Belur Industrial Area,Dharwad-580011 (KARNATAKA) **INDIA**

Vadodara Works:- 67-A,G.I.D.C,Majusar,Savli,Vadodara-397115 (GUJARAT) **INDIA**